



# PATHWAY STABILIZER

## Proper Installation References

### A general guide for your customers

#### AGGREGATE SELECTION\*

##### DETERMINING THE RIGHT AGGREGATE FOR INSTALLATION OF TECHNISOIL®

#### What aggregate works best with TechniSoil®?

Most crushed stone mixes that contains 8-18% stone dust/screenings and angular aggregates. 3/8" minus material is most commonly used for pathways and patios. 1/2-3/4" minus material is recommended for high use areas.

#### Will sand, stone dust/ granite screenings, river rock or screened aggregates work with TechniSoil®?

No, these materials are unsuitable and will not work with TechniSoil®.

#### PROPER AGGREGATE

- ✓ Crushed Stone  
3/8th" minus, 1/2" minus & 3/4" minus
- ✓ Decomposed Granite
- ✓ Crusher Run/ABC

#### IMPROPER AGGREGATE

- ✗ Screened Aggregates
- ✗ River Rock
- ✗ Sands
- ✗ High Clay Content
- ✗ Granite Screenings
- ✗ Crusher Fines

\* If your aggregate is not listed or you need assistance in determining the proper aggregate, please call 877-356-2250 x2

#### PROPER COMPACTION

#### What compaction devise is recommended?

A vibratory plate compactor. A hand tamer can be used in corners and hard to reach areas. For larger application areas a double drum roller can be used.

#### I have waited 30-45 minutes after applying TechniSoil®, but the surface is still very wet. Do I still compact?

Additional drying time is needed. Clouds, shading from trees/buildings or cool temperatures will require additional drying time. Compact when surface is partially dry.

#### How many times do I need to compact the surface?

3 passes will create a more durable surface. If ridges from the compactor occur, a second pass will often alleviate this issue. A hand-tamper can also be used to smooth the surface.

#### APPLICATION RATES\*

<b>5 gallon Pail</b>	50 sq. ft. / pail
<b>55 gallon Drum</b>	550 sq. ft. / drum
<b>275 gallon Tote</b>	2,750 sq. ft. / tote

\* Estimated Coverage Rates

#### ADDITIONAL RESOURCES

##### Pathway Troubleshooting

TechniSoil.com/pathway-help

##### Weather Tips

TechniSoil.com/weather-tips

##### Maintenance Help & Tips

TechniSoil.com/misc-help

##### Video References

TechniSoil.com/video

##### Phone

877-356-2250, Prompt #2

##### E-mail

technical@TechniSoil.com

##### Web

TechniSoil.com

**TECHNISOIL MUST BE APPLIED OVER A PREPARED SUB-BASE OF 2-3" CRUSHED STONE. DO NOT APPLY TECHNISOIL WITHOUT A PROPER BASE.**